



Transocean Alkyd Barrier

Code: 7321

Product description.

An alkyd undercoat loaded with non-toxic pigments for an excellent protection in marine environments. It provides good hiding power and adheres well to various alkyd priming systems.

Technical properties.

| | |
|----------------------------|--------------|
| Colour/Texture | White/ Mat |
| Volume Solids | 48% |
| Specific gravity | 1.47 gr/ml |
| Volatile organic compounds | 410 gr/liter |
| Flashpoint | >35°C |

Surface Preparation

Coated substrates - Existing systems should be dry and free from loose paint, salt, grease and other contaminants prior to overcoating.

High pressure wash with fresh water and allow thorough drying.

Corroded and/or damaged areas should be repaired first with an appropriate primer system such as Transocean Alkyd Primer 7122.

Usage instructions

Substrate should be dry and free from contaminations.

Relative Humidity should be less than 90 %RH.

Thin if necessary with the specified thinner. Mix well preferably by means of a mechanical stirrer.

When applied by brush or roller, apply in smooth and gentle strokes. Apply crosswise to ensure an even distribution of the paint.

When applied by airless or airspray observe spraying recommendations mentioned on the next page.

Avoid excessive application as it will result in sagging and a poor appearance.

Apply two coats.

Whether applying by brush, roller or spray, wear protective clothing, goggles and gloves. Refrain from smoking at all times. For further information refer to label instruction or safety data sheet please.

Application data.

| | |
|-----------------------------|-------------------------------|
| Dry film thickness per coat | 40 micron |
| Wet film thickness per coat | 85 micron |
| Theoretical coverage | 12 sq.m/liter |
| Thinner | Transocean Alkyd Thinner 7600 |
| Surface Temperature | Minimum 0°C Maximum 40°C |

Spray equipment data.

| | Conventional spray | Airless spray |
|--|--------------------|----------------|
| Nozzle orifice | 1.2 – 2.0 mm | 0.38 – 0.53 mm |
| Air pressure | 3 – 5 bar | 120 – 180 bar |
| Volume of thinner | 0 – 15% | 0 – 3 % |
| Practical Spreading rate (m ² /l) | 6.6 | 8.4 |

Drying and recoating times.

| Substrate temperature | Dry to recoat | Fully cured | Maximum recoating (1) |
|-----------------------|---------------|-------------|-----------------------|
| 10 °C | 24 hours | 2 days | Indefinite |
| 23 °C | 16 hours | 2 days | Indefinite |
| 30 °C | 8 hours | 1 day | Indefinite |

(1) The surface should be dry and free from salts and other contaminants prior to overcoating. The best intercoat adhesion is achieved when the subsequent coat is applied before the preceding coat is fully cured. After prolonged exposure times it may be necessary to roughen the surface in order to ensure intercoat adhesion. When in doubt, consult your nearest Transocean office.

Health and safety.

Observe the precautionary notices on the label of the container. A material safety data sheet is available upon request and national or local safety regulations should be followed. As a general rule, avoid skin- and eye contact by wearing overalls, gloves, goggles, mask, etc. Spillage on the skin should immediately be removed by thorough washing with lukewarm water and soap or a suitable industrial cleaner. Eyes should be flushed with fresh water and medical attention sought immediately.

Spraying should be carried out under well-ventilated conditions. Avoid inhalation of solvent vapours and paint mist by wearing an air mask.

This product contains flammable materials and should be kept away from sparks and open flames. Smoking in the area should not be permitted.

Worldwide availability

The product is part of the common Transocean product range but local availability is subject to confirmation. Although we strive to supply the same product through the world, slight modifications of the product in some cases may be necessary in order to comply with local conditions and/or national regulations. In such cases an alternative datasheet will be issued.

Disclaimer

The information in this data sheet is provided to the best of our knowledge. However, we have no control over either quality or condition of the substrate and other factors affecting the use and application of this product. Therefore, we cannot accept any liability whatsoever or howsoever arising from the performance of the product or for any loss or damage arising from the use of this product.

We reserve the right to change the product without notice.

Date of issue: August, 06.